


- ☐ Petition for () month(s) extension of time pursuant to 37 C.F.R. §§ 1.17 and 1.136(a). \$0.00 for the extension of time.
- ☒ No fee is required.
- ☐ Check(s) in the amount of \$0.00 is(are) enclosed.
- ☐ Please charge Deposit Account No. 02-2448 in the amount of \$0.00. This form is submitted in triplicate.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By 
Marc S. Weiner, #32,181
P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

MSW/sh
0992-0124P

Attachment(s)

(Rev. 10/15/02)



PATENT
0992-0124P

suppl
#10
3/4/03
H

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Hideshi KAWACHI et al. Conf.: 1370
Appl. No.: 09/637,067 Group: 1711
Filed: August 11, 2000 Examiner: Mullis
For: MULTILAYERED ARTICLE, VESSEL AND RESIN
COMPOSITION BASED ON POLYETHYLENE

SUPPLEMENTAL AMENDMENT

FEB 14 2003

Assistant Commissioner of Patent
Washington, D.C. 20231

Sir:

Further to the Amendment filed January 21, 2003, the following supplemental amendments and remarks are respectfully submitted in connection with the above-identified application.

RECEIVED
FEB 24 2003
1000 MAIL ROOM

IN THE CLAIMS:

Please amend the following claims:

Claim 12 (Twice Amended) A resin composition (c) which is based on polyethylene, comprising

99-65% of a polyethylene resin (a1) having a melt flow rate (MFR) according to ASTM D 1238 (190°C, 2160 g load) in the range from 0.001 to 0.5 g/10 min. and a density in the range from 0.945 to 0.980 g/cm³,

0.5-15% of a modified ethylene/ α -olefin copolymer (a2) which is modified by having grafted thereon an unsaturated dicarboxylic acid or its anhydride

D1
cmf